

## **LISTING OF THE CLAIMS**

Claims 1-5 (canceled)

Claim 6 (currently amended): A substrate/film composite comprising a substrate and a multilayer film comprising an outer heat-sealable polyolefin layer, a core gas-barrier layer comprising at least one gas-barrier resin selected from the group consisting of EVOH and polyamide, and an outer bonding layer comprising at least one styrene-based polymer, wherein:

- (a) the at least one styrene-based polymer makes up at least 35 weight percent of the film, based on total film weight;
- (b) the styrene-based polymer comprises modified styrene-based polymer having polar groups thereon;
- (c) the modified styrene-based polymer is present in a ratio, with respect to the weight of the gas-barrier resin, of at least 0.1 : 1; and

wherein the multilayer film has an overall thickness of from about 10 microns to 80 microns, and wherein the substrate comprises foam.

Claim 7 (canceled)

Claim 8 (previously presented): The substrate/film composite according to Claim 7, wherein the foam substrate comprises substrate/film composite reclaim in an amount of from about 0.001 percent up to about 100 percent, based on foam substrate weight.

Claim 9 (canceled)

Claim 10 (original): The substrate/film composite according to Claim 8, wherein the foam substrate comprises substrate/film composite reclaim in an amount of at least 20 percent, based on weight of foam substrate.

Claim 11 (original): The substrate/film composite according to Claim 10, wherein the foam substrate comprises substrate/film composite reclaim in an amount of at least 30 percent, based on weight of foam substrate.

Claim 12 (original): The substrate/film composite according to Claim 11, wherein the foam substrate comprises substrate/film composite reclaim in an amount of at least 40 percent, based on weight of foam substrate.

Claim 13 (original): The substrate/film composite according to Claim 12, wherein the foam substrate comprises substrate/film composite reclaim in an amount of at least 50 percent, based on weight of foam substrate.

Claim 14 (original): The substrate/film composite according to Claim 13, wherein the foam substrate comprises substrate/film composite reclaim in an amount of at least 60 percent, based on weight of foam substrate.

Claim 15 (canceled)

Claim 16 (previously presented): A tray comprising a substrate/film composite comprising a foam substrate and a liner comprising a multilayer film having an outer heat-sealable polyolefin layer, a core gas-barrier layer comprising at least one gas-barrier resin selected from the group consisting of EVOH and polyamide, and an outer bonding layer comprising at least one styrene-based polymer, wherein:

- (a) the at least one styrene-based polymer makes up at least 35 weight percent of the film, based on total film weight;
- (b) the styrene-based polymer comprises modified styrene-based polymer having polar groups thereon;
- (c) the modified styrene-based polymer is present in a ratio, with respect to the weight of the gas-barrier resin, of at least 0.1 : 1; and

wherein the multilayer film has an overall thickness of from about 10 microns to 80 microns.

Claim 17 (original): The tray according to Claim 16, further comprising a bottom portion and side walls integral with the bottom portion, and a flange extending outwardly from top edges of the side walls.

Claim 18 (original): The tray according to Claim 17, wherein the flange extends outwardly in a plane parallel to the bottom portion.

Claim 19 (previously presented): A food package comprising:

(A) a tray comprising a substrate/film composite comprising a foam substrate and a liner comprising a multilayer film having an outer heat-sealable polyolefin layer, a core gas-barrier layer comprising at least one gas-barrier resin selected from the group consisting of EVOH and polyamide, and an outer bonding layer comprising at least one styrene-based polymer, wherein:

- (i) the at least one styrene-based polymer makes up at least 35 weight percent of the film, based on total film weight;
- (ii) the styrene-based polymer comprises modified styrene-based polymer having polar groups thereon;

(iii) the modified styrene-based polymer is present in a ratio, with respect to the weight of the gas-barrier resin, of at least 0.1 : 1; and

wherein the multilayer film has an overall thickness of from about 10 microns to 80 microns;  
and

(B) a food product on an upper surface of the tray; and

(C) a film over the food product, the film being sealed along the flange of the tray.

Claim 20 (previously presented): The substrate/film composite according to Claim 6, wherein the substrate comprises polystyrene.

Claim 21 (previously presented): The multilayer film according to Claim 1, wherein the multilayer film has an overall thickness of from about 15 microns to 80 microns.

Claim 22 (previously presented): The multilayer film according to Claim 1, wherein the multilayer film has an overall thickness of from about 20 microns to 60 microns.